



試驗報告

報告編號: KV-22-00846 數: 1 OF

報告日期:111年 02月 18日

黏輕人企業有限公司

產品名稱: 1688 建築用密封材料 送驗廠商: 黏輕人企業有限公司 收件日期: 111年 01月 26日

試驗日期: 111年 01月 26日~111年 02月 18日

註: 1.以上資料(樣品名稱、送驗人員、會驗人員、試驗方法、試驗數量、收件日期及

試驗日期除外)及下述報告內容標示#處係由顧客提供

2.除非另有說明,此報告結果僅對測試之樣品負責

未經本公司事先書面同意,此報告不可部分複製

試驗結果:

777					
試驗項目			試驗方法	試驗結果	
抗垂流性(mm)	縱向	5 °C/24 h	CNS 8904(2011)	0	
	横向	5 °C/24 h		0	
抗拉強度(kgf/cm²)			參照 CNS 3553(1996)	9.5	
延伸率(%)			(3 號形,V= 500 mm/min)	420	
撕裂強度(kgf/cm)			參照 CNS 3559 (2007)	5.0	
			(C 型,V= 500 mm/min)		

----- 1 -----

本報告若有提供規範值,該規範值僅供參考,合格之判定以委託單位實際要求為準

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com.tw/Terms-and-Conditions and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com.tw/Terms-and-Conditions. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested

TWD 4391648





試驗報告

報告編號: KV-22-00846 數: 2 OF

報告日期:111年 02月 18日

試驗結果:

試驗項目	試驗方法	試驗結果
硬度(Type A/1sec)	參照 CNS 3555(2008)	24
比重(25 °C)	CNS 8904(1982)	1.264
不沾黏時間 (h)	ASTM C679-03(2009) ^{ε1}	0.5

註:1.本試驗樣品為單液型。

- 2.本試驗報告不沾黏時間試驗為 TAF 認證範圍,其餘則非。
- 3.本試驗報告之試驗地點同實驗室地址。

樣品照片:



---- 000 -----

本報告若有提供規範值,該規範值僅供參考,合格之判定以委託單位實際要求為準

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com.tw/Terms-and-Conditions and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com.tw/Terms-and-Conditions. Attention is drawn to the limitation of liability, indeminification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

TWD 4391649

SGS Taiwan Ltd. | No.61, Kai Fa Rd., Nanzih District, Kaohsiung City 811637, Taiwan /811637高雄市楠梓區開發路61號 f (886-7) 301-1165 www.sgs.com.tw